

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2001-354988

(43)Date of publication of application : 25.12.2001

(51)Int.Cl.

C10M171/00  
C10M101/02  
C10M105/04  
C10M105/20  
C10M105/34  
C10M105/48  
C10M107/02  
C10M125/24  
C10M129/32  
C10M129/40  
C10M133/06  
C10M133/08  
C10M133/16  
C10M133/44  
C10M133/54  
C10M133/56  
C10M133/58  
C10M137/02  
C10M137/04  
C10M137/08  
C10M137/10  
// C10N 10:04  
C10N 20:00  
C10N 20:02  
C10N 20:04  
C10N 30:04  
C10N 30:06  
C10N 30:10  
C10N 40:04

(21)Application number : 2000-175708

(71)Applicant : NIPPON MITSUBISHI OIL CORP

(22)Date of filing : 12.06.2000

(72)Inventor : SHIRAHAMA SHINICHI  
OKAWA TETSUO

## (54) FLUID COMPOSITION FOR TRACTION DRIVE

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a fluid composition for traction drives which is applicable not only to a power-transmission system but also to a hydraulic control system and a friction property control system using a wet clutch.

SOLUTION: This fluid composition for traction drives is prepared by compounding (A) a base oil having a traction coefficient of  $\geq 0.05$  with (B) from 0.01 to 10 mass %, based on the total weight of the composition, one or more oils selected from the following (B-1) and (B-2), (B-1) a mineral oil having a dynamic viscosity at 100° C of from 1.5 to 5.0 mm<sup>2</sup>/s and a pour point of  $\leq -20^{\circ}$  C, (B-2) a synthetic oil having a dynamic viscosity at 100° C of from 1.3 to 3.0 mm<sup>2</sup>/s and a low-temperature viscosity at -40° C of  $\leq 2,000$  mPa.s.

## LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office